



Technical Data Sheet

CRAMOLIN® ZINC SPRAY Art. No. 127

Product description

ZINC is a cold galvanizing zinc-rich coating for corrosion and rust protection. It forms a tough and flexible film which actually bonds with any base metall. The film contains 99, 5% pure zinc pigments and bonds electrochemically to bare metal. The coating provides active galvanic protection and stops rust formation even when scratched or abraded. The coating is fast drying, shows excellent adherence and forms a grey layer. ZINC meets DIN 50976 and Mil. Specs. P-26915C, P-46105 and P-21035B

Application

Particularly suitable for corrosion protection of structural steel, steel buildings, steel roofs, windows and doors, touch up over galvanized coatings, welding seams and spot welding, home and garden equipment, air conditioners, cooling towers and agricultural equipment.

Please note

Spray only on clean and dry surface to guarantee the maximum galvanic protection. Remove loose scale with a wire brush. Remove grease and dirt with DEGREASER or ELECTRO CLEANER OS. Shake well until mixing balls are free. Spray on the whole surface of parts to be treated, maintaining a distance of approximately 30 cm, otherwise the layer applied will flow. The lacquer will be dry to permit handling after 30 min, and fully cured after approx. 24 hours. The spray nozzle has a self-cleaning action. Should it nevertheless get clogged, clean it using solvent.



Technical Data

Color:	grey
Specific gravity (20° C):	0,95[g/cm ³]
Drying conditions at:	30 min dry to touch
Room temperature:	24 h totally cured
Temperature resistance:	up to + 500°C
Salt spray resistance:	ca. 600 – 800 h (DIN 53167 + DIN 50021)
Ideal film thickness:	60 – 80 [µm]
Purity of zinc pigment:	99,5%

Storage / Shelf Life

Shelf life is 2 years if stored correctly. Package after emptying to be disposed via metal scrap.

ITW Chemische Produkte GmbH Co. KG
Mühlacker Strasse 149, D-75417 Mühlacker
Telefon +49 7041 96 34 0, Telefax +49 7041 96 34 29
e-mail info@itwcp.de, website www.itwcp.de
January 2010