Technical Datasheet



Article No. 14-98

Article Cyanoacrylate Adhesive Special

Available sizes

20g, 50g, other sizes upon request

Product description / Please note

VARYBOND® Grade 14-98 is a relative high viscous, modified cyanaoacrylic adhesive which shows improved impact resistance combined with excellent properties in terms of peel strength and temperature cycles. The product performs very well on metals, ferrite, ceramic, most of nowadays used plastics and all combinations among each other.

Application

The parts should be dry, clean and free of any kind of grease so that the best result can be acheived. Apply directly from the bottle.

Pysical Properties

Liquid Product Chemical Base Colour Viscosity mPas @ 25°C Density g/cm³ (DIN 51757) Flash point (DIN 55213) Shelf life Fixture time on Aluminium / Aluminium SBR / SBR - rubber

EPDM / EPDM - rubber Final strength

Cured Product

Rensile Shear strength on Aluminium / Aluminium

Shore D hardness Elongation Thermal range Melting point a-Cyanoacrylicacid-ethylester clear / colourless 500 - 700 1,04 87 °C 12 months when stored correctly

20 - 40 seconds 10 - 15 seconds 14 - 20 seconds 24 hours

> 26 N/mm² (DIN EN 1465)

70 - 80 > 12% - 30°C up to + 80°C +165°C

Storage / Shelf life

Package should not be mixed with other materials. Shelf life is up to 12 months if stored correctly under 10°C. Package after emptying to be disposed via metal scrap.